



The Experts in Wood Care

All Conference® Gym Finish 50% Polyurethane

PRODUCT INFORMATION

Description: All Conference® Gym Finish is a solvent-based polyurethane finish specially formulated for wood sport floors. This premium performance product will provide the highest durability & wet-look gloss that you would expect from the ‘Experts in Wood Care’. All Conference® Gym Finish is low in viscosity so it is easy to use regardless of application method.

Caution- Floors may become slippery when wet. Use proper caution signs & remove spill or standing water immediately. This product is not recommended for exterior use.

Directions for Use:

Application for Recoat (refer to the Magee Procedure Guide for complete instructions)

1. Thoroughly sweep or dust mop the floor, scrape or remove gum or debris.
2. Dry abrade the floor 100 grit screens & 175rpm swing machine.
3. Tack the floor with water & clean towels to remove all residue.
4. Allow the floor to dry thoroughly.
5. Apply All Conference® Gym Finish with a K-200 EZ Way Applicator or a heavy weight T-bar applicator.
6. Allow 8-16 hours to dry (conditions may vary dry time, ensure floor is tack-free before proceeding with the next coat).
7. If more than 24 hours elapsed after 1st coat, dry abrade the floor & tack with water.
8. Apply the 2nd coat of All Conference® Gym Finish.
9. Allow floor to cure 24-48 hours before opening to light traffic.
10. Allow a minimum of 5 days before opening to regular use.

Maintenance

1. Dust mop daily with Waterthane® Dust Mop Treatment.
2. Use Magee® Speed Mop weekly, or as needed, with No Streak Floor Cleaner.

Specifications:

Color: Light amber

Odor: Solvent

Solids: 49-51%

Cure Rate: 14 days

Viscosity: A2-A

Flash Point: <105°F

Dry Time: 8-16 hours

VOC: <450 g/l

Coverage Rate: 500-600 sq ft/gal

Shelf Life: 2 years

HMIS	Rating
Health	2
Flammability	2
Reactivity	0
Personal Protection	-

Keep Out Of Reach Of Children
For Commercial & Industrial Use Only