



## Product Information

# GYM FLOOR MARKING ENAMELS

### DESCRIPTION

GYM FLOOR MARKING ENAMELS are tough, lead free, wear resistant, high gloss, oil modified urethane enamels for use in lining and marking basketball or other wood floors for athletic events. They are ideal for color in the free throw or center jump circle and may also be used as a border for the basketball floor to provide color contrast with the playing area. They conform to OSHA color standards.

GYM FLOOR MARKING ENAMELS have a V.O.C. content of 450 gm/l. FOR PROFESSIONAL USE ONLY.

COVERAGE: Approximately 600 linear feet of 2" line or 1200 feet of 1" line per quart. For solid areas, approximately 100 sq. ft. per quart.

### IMPORTANT NOTES

1. Do not apply product if temperature exceeds 90°F and humidity is 80% or above. In conditions of very high temperature and humidity, these products will not cure properly, resulting in a nonuniform appearance.
2. Not recommended for use with either moisture cured urethane or catalyzed epoxy sealers or finishes.

**NOTICE: TO COMPLY WITH V.O.C. REGULATIONS MANY MANUFACTURERS HAVE REFORMULATED THEIR PAINT. WE CAN NO LONGER BE RESPONSIBLE FOR ANY PEELING OR OTHER PROBLEMS OF OUR VARNISHES WITH PAINTS EXCEPT OUR OWN BRANDS.**

### DIRECTIONS

#### SEALED WOOD FLOORS

1. Clean floor thoroughly to remove all soil.
2. Abrade floor with 120 grit screen to remove gloss. Sweep and tack rag to remove fine particles of dust.
3. Apply tape making sure edges are tight to floor.
4. Stir product well before using. Apply with a natural hair bristle brush or short nap mohair roller. If a second coat is required apply after first coat is tack free. As soon as paint has set pull off tape to avoid jagged lines.
5. Let GYM FLOOR MARKING ENAMELS cure 24 hours before applying finish.
6. Abrade painted areas lightly with maroon pad to remove gloss. Do not use floor machine to abrade freshly painted areas.
7. Apply ALL CONFERENCE (M50) or CURE-O-THANE FINISH (M17) .

#### NEWLY SANDED FLOORS

1. Apply two coats of CURE-O-THANE SANDING SEAL (M16). Abrade after each coat with 120 grit screen. Sweep and tack rag.
2. Proceed with steps 3 through 7 above.

Brushes and equipment should be cleaned with WOOD KLEEN (M105). Thinning of these products is not recommended.

**WARNING:** Combustible. Contains Petroleum Distillate. Keep away from heat, sparks and all flames, including but not limited to pilot lights. Open doors and windows for cross-ventilation. Close container after each use. Cloths used with this product are combustible and should be discarded in closed metal containers placed outdoors. Harmful Or Fatal If Swallowed: Do not take internally. Eye And Skin Irritant: Avoid prolonged or repeated contact with skin. FIRST AID: If swallowed, do not induce vomiting. Call a physician immediately. If in eyes, flush thoroughly with water for at least 15 minutes, then see a doctor. For skin, wash with soap and water. If irritation persists, see a doctor.

Keep Out Of Reach Of Children For Industrial & Institutional Use Only

### SPECIFICATIONS

Type.....	Oil modified urethane	Dry hard.....	Overnight
OSHA colors.....	White, Green, Black, Blue, Red, Yellow, Orange	After tack.....	None
Flash point.....	Greater than 105°F	Adhesion of overcoats (with abrasion).....	Excellent
Set to touch.....	2-3 hours	Color retention.....	Excellent
Dust free.....	4-6 hours	Gloss.....	Excellent
		V.O.C. ....	450 gm/l